

RECEIVED  
CENTRAL FAX CENTER  
DEC 26 2006

**Amendments to the Claims:**

This listing of claims will replace all prior versions, and listings, of claims in the present application:

**Listing of Claims:**

Claim 1. (Canceled).

2. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein the protective substance includes at least one of a non-alkaline metal, a non-earth alkaline metal, an oxidizable metal compound of non-alkaline metals, an oxidizable metal compound of non-earth alkaline metals, phosphate and phosphorous.

3. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein the protective substance includes at least one of zinc, an oxidizable iron oxide and elemental aluminum.

4. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein the protective substance is in a proportion of at least 30% by volume.

5. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein the protective substance is in a proportion of at least 50% by volume.

6. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein the protective substance is in a proportion of at least 70% by volume.

7. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein a starting material of the corrosion protective lacquer includes a clear lacquer.

8. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein a starting material of the corrosion protective lacquer includes an organic solvent.

9. (Currently Amended) The corrosion protective brake lacquer according to claim 8, wherein the corrosion protective lacquer includes a water-based lacquer.

10. (Currently Amended) A corrosion protective brake lacquer for producing a corrosion protective coating composition for a braking surface of at least one of a brake disk and a brake drum, comprising:

a protective substance configured to at least one of chemically react with oxygen and bind with oxygen;

wherein the protective substance has an average grain size that is substantially equal to at least one of a maximum roughness and an average size of score marks of the braking surface of the at least one of the brake disk and the brake drum.

Claim 11. (Canceled).

12. (Currently Amended) The corrosion protective brake coating composition according to claim 17, wherein the protective substance includes at least one of a non-alkaline metal, a non-earth alkaline metal, an oxidizable metal compound, phosphate and phosphorous.

13. (Currently Amended) The corrosion protective brake coating composition according to claim 17, wherein the protective substance includes at least one of zinc, oxidizable iron oxide and elemental aluminum.

14. (Currently Amended) The corrosion protective brake coating composition according to claim 17, wherein the protective substance in the corrosion protective coating composition has a proportion of at least 30% by volume.

15. (Currently Amended) The corrosion protective brake coating composition according to claim 17, wherein the protective substance in the corrosion protective coating composition has a proportion of at least 50% by volume.

16. (Currently Amended) The corrosion protective brake coating composition according to claim 17, wherein the protective substance in the corrosion protective coating composition has a proportion of at least 70% by volume.

17. (Currently Amended) A corrosion protective brake coating composition for a braking surface of at least one of a brake disk and a brake drum, comprising:

a lacquer including a protective substance that at least one of chemically reacts with oxygen and binds with oxygen;

wherein the protective substance has an average grain size substantially equal to at least one of a maximum roughness, an average pore diameter and an average size of score marks of the braking surface of the at least one of the brake disk and the brake drum.

Claims 18 to 26. (Canceled).

27. (Currently Amended) The corrosion protective brake lacquer according to claim 10, wherein a starting material of the corrosion protective lacquer includes a tinted lacquer.

Claims 28 to 30. (Canceled).

31. (Currently Amended) A corrosion protective brake coating composition for a braking surface of at least one of a brake disk and a brake drum, comprising:

a lacquer including a protective substance that at least one of chemically reacts with oxygen and binds with oxygen and that is configured to fill one of a pore and a score of average size on the braking surface of the at least one of the brake disk and the brake drum upon abrading the corrosion protective coating composition by a brake lining during braking.

Claims 32 to 37. (Canceled).